



IN THE UNITED STATES PATENT & TRADEMARK OFFICE

Application Number : 09/843,166 Confirmation No. 8587
Applicant : Mitchell Corner et al.
Filed : April 27, 2001
Tech Cntr/AU : 1764
Examiner : Ellen M. McAvoy
Entitled : Lubricant Compositions
Attorney Reference : 090128-0280189
Customer Number : 00909

MAIL STOP ISSUE FEE

Commissioner for Patents
P.O. Box 1450
Alexandria, Virginia 22313-1450

SUBMISSION OF PRIORITY DOCUMENT


Attached please find the certified copy of the following foreign application from which priority is claimed for this case:

<u>Country</u>	<u>Application Number</u>	<u>Filing Date</u>
Great Britain	9823455.2	October 28, 1998

Date: April 12, 2004

PILLSBURY WINTHROP LLP
P.O. Box 10500
McLean, VA 22102
Telephone: (703) 905-2000
Facsimile: (703) 905-2500

Customer Number: 00909


Richard A. Steinberg
Registration No. 26,588



INVESTOR IN PEOPLE

The Patent Office
Concept House
Cardiff Road
Newport
South Wales
NP10 8QQ

I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.

In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.

Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.

Signed *AmBrewer*

Dated 2 April 2004

Request for grant of a patent

(See the notes on the back of this form. You can also get an explanatory leaflet from the Patent Office to help you fill in this form)

The Patent Office

Cardiff Road
Newport
Gwent NP9 1RH

1. Your reference

MTW 58684

2. Patent application number

(The Patent Office will put in a number for you)

9823455.2

28 OCT 1998

3. Full name, address and postcode of the or of each applicant (underline all surnames)

IMPERIAL CHEMICAL INDUSTRIES PLC
Imperial Chemical House
Millbank
London
SW1 3JF

Patents ADP number (if you know it)

If the applicant is a corporate body, give the country/state of its incorporation

UK

4. Title of the invention

LUBRICANTS

5. Name of your agent (if you have one)

"Address for service" in the United Kingdom to which all correspondence should be sent (including the postcode)

CHRISTOPHER ROBERT MILLROSS
ICI Group Intellectual Property
P O Box 90
Wilton
Middlesbrough
TS90 8JE

Patents ADP number (if you know it)

6. If you are declaring priority from one or more earlier patent applications, give the country and the date of filing of the or of each of these earlier applications and (if you know it) the or each application number

Country

Priority application number
(if you know it)

Date of filing
(day / month / year)

7. If this application is divided or otherwise derived from an earlier UK application, give the number and the filing date of the earlier application

Number of earlier application

Date of filing
(day / month / year)

8. Is a statement of inventorship and of right to grant of a patent required in support of this request? (Answer 'Yes' if:

YES

- a) any applicant named in part 3 is not an inventor, or
 - b) there is an inventor who is not named as an applicant, or
 - c) any named applicant is a corporate body.
- See note (d))

Patents Form 1/77

9. Enter the number of sheets for any of the following items you are filing with this form. Do not count copies of the same document

Continuation sheets of this form

Description 3

Claim(s) 0

Abstract 0

Drawing(s) 0

10. If you are also filing any of the following, state how many against each item.

Priority documents

Translations of priority documents

Statement of inventorship and right to grant of a patent (Patents Form 7/77)

Request for preliminary examination and search (Patents Form 9/77)

Request for substantive examination (Patents Form 10/77)

Any other documents (please specify)

11.

I/We request the grant of a patent on the basis of this application.

Signature

Date

26/10/1984

12. Name and daytime telephone number of person to contact in the United Kingdom

Christopher Robert Millross
01842 437843

Warning

After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least 6 weeks beforehand in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been given, or any such direction has been revoked.

Notes

- If you need help to fill in this form or you have any questions, please contact the Patent Office on 0645 500505.*
- Write your answers in capital letters using black ink or you may type them.*
- If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.*
- If you have answered 'Yes' Patents Form 7/77 will need to be filed.*
- Once you have filled in the form you must remember to sign and date it.*
- For details of the fee and ways to pay please contact the Patent Office.*

LUBRICANTS

This invention relates to lubricants, in particular to lubricants for air compressors based on a blend of a polyalkylene glycol and an ester.

Such blends, which have been described in US 4302343, EP 17072, US 4751012 and EP 227477 offer benefits over the conventional mineral oil type lubricants in terms of thermal and oxidative stability, reduced deposit formation, improved lubricity and increased service intervals.

Blends of lower alcohol initiated propoxylates or polypropylene glycol, combined with an aviation type neopentyl polyol ester or diacid ester which are available commercially perform well across a range of performance criteria such as low temperature fluidity and foaming tendency.

However, there are problems with these commercial products due to a tendency to form stable emulsions when mixed with water and it is an unfortunate fact that such mixing is unavoidable, unless air compressors are run in perfectly dry air conditions, due to the moisture in the air condensing out.

Emulsion formation can affect lubrication performance as well as the ability to measure the lubricant level.

Moreover, unlike conventional mineral oils, where the 'condensate' is easily separated from the oil and can be disposed of as water, 'condensate' containing emulsified lubricant is now considered as 'chemical' waste with all the associated costs of disposal.

The presence of water can also cause a reduction in the viscosity of the lubricant (affecting lubricant performance) and a change in the acid value which can increase the possibility of corrosion.

Clearly, the degree to which the lubricant takes up water is of great relevance.

A further problem can arise if such products are incorrectly added to a compressor containing mineral oil due to low miscibility with mineral oil.

It has been found that these problems can be overcome without detrimentally affecting other properties by blending specific polyalkylene glycols with specific esters.

According to one aspect of the invention there is provided a lubricant composition comprising a polyalkylene glycol having the formula

$\text{R O} - (\text{CH}_2\text{CH}(\text{CH}_3)\text{O})_n - \text{CH}_3$ where $\text{R} = \text{C1 to C15 alkyl}$, preferably C1-4 , more preferably C1 and $n = 1 \text{ to } 35$, preferably $8 \text{ to } 30$,

and an ester.

According to a preferred aspect, the ester is a phthalate, a polyol ester, a diacid ester, or a trimellitate; the preferred phthalates are di-isodecyl phthalate, or 355 trimethyl hexyl phthalate.

Preferably, the composition contains an antifoam agent, an antioxidant and/or an anticorrosion agent.

The invention will be more readily understood from the following examples.

Example 1

Tests were carried out using a modified form of ASTM D1401 (a common industry test used as a measure of the demulsibility of lubricant/water mixtures) in which 40 parts by vol of lubricant and 40 parts by vol of water were mixed together to form an emulsion and left to stand.

The results, which together with comments are shown in the Table are based on x-y-z (t) where x is the volume of the oil layer, y is the volume of the water layer, z is the volume of the emulsion layer and t is the time taken to achieve the result; t = 5 is the minimum time for the test and so 40-40-0(5) is the ideal result.

Table 1

Demulsibility (ASTM D1401) - Esters/PAG Combinations							
Sample	Blend Ratio	Result	Oil	Water	Interface	Emulsion	Pass/
1	60:40	1-8-71(60)	cloudy	hazy	well defined	milky	Fail
2	60:40	0-5-75(30)	none	hazy	well defined	milky	Fail
3	53:47	40-40-0(5)	hazy	hazy	well defined	milky	Pas
4	70:30	0-38-42(30)	none	cloudy	well defined	milky	Fail
5	52:48	40-40-0(30)	hazy	clear	well defined	milky	Pas
6	52:48	40-40-0(30)	hazy	clear	well defined	milky	Pas
7	55:45	40-40-0(10)	hazy	clear	well defined	milky	Pas
All include 0.6% commercial antioxidant & anticorrosion package							

Sample 1 = a commercially available blend of butanol initiated propoxylate and pentaerythritol ester

Sample 2 = a commercially available blend of butanol initiated propoxylate and adipate ester

Sample 3 = a blend of methanol initiated methyl end capped propoxylate and a tetra ester of pentaerythritol and 2-ethyl hexanoic acid

Sample 4 = a blend of butanol initiated propoxylate and a tetra ester of pentythritol and 2-ethyl hexanoic acid

Sample 5 = a blend of methanol initiated methyl end capped propoxylate and isodecyl phthalate

Sample 6 = as Sample 5 plus non- silicone antifoam agent

Sample 7 = a blend of methanol initiated methyl end capped propoxylate and 355 trimethyl hexyl phthalate

In respect of low temperature fluidity, measured as the pour point, i.e. the minimum temperature at which the lubricant could be poured, Samples 5, 6 and 7 (i.e those of the invention) were better (Pour Point -42°C) than the commercially available Sample 2 (Pour Point -38°C).

Although Samples 5, 6 and 7 had a greater tendency to foam than Sample 1, such foaming could be controlled to achieve similar results by the addition of 50 ppm of, a commercially available, non-silicone antifoaming agent.

In respect of miscibility, Sample 1 was only miscible with oil at a 10% content whereas Sample 5 was miscible up to a content of 25%.

The effect of water on the viscosity and corrosivity was measured using the Beverage Bottle Test (based on a modified version of ASTM D2619) in which the changes in viscosity and acid value of a mixture of 75g sample and 25g water were measured after a period of 2 weeks.

The viscosity (cst at 40°C) was reduced by 3.1 in the case of Sample 1 whereas for Sample 6 the reduction was only 0.6. Similarly, the acid value (mgKOH/g) changed to a greater extent for Sample 1 (0.54) than for Sample 6 (0.01).

To assess the water take up, samples were dried using a nitrogen purge until the water content measure 100ppm. Samples were then placed in dessicators at 75°C and the water content measured at intervals.

For both Samples 1 and 6, the water content rose steadily until reaching a constant level after circa 30 days. However, whereas the content of sample 1 was circa 6000 ppm, the content of sample 6 was only 4000 ppm.